



Primer and Sealer

Product Data/ Application Instructions

 Primer for concrete surfaces prior to application of Nu-Klad 100A and epoxy surface finishes.

Typical Uses

Nu-Klad 105 primer and sealer is recommended for priming and sealing of concrete surfaces for Nu-Klad 100A and epoxy surfacers and top coats. Nu-Klad 105 is compatible with damp concrete surfaces. Nu-Klad can also be used as a liquid membrane curing compound for concrete and meets the moisture retention requirements of ASTM C309

Outstanding Characteristics

Tideguard 171A forms a tough barrier providing long lasting protection: in continuous or intermittent immersion; against repeated splash wetting and wave action and in salt air exposure. Protects also against costly damage due to impact and abrasion from workboats, debris and ice. Provides a tough, abrasion resistant, non skid surface.

Can be exposed to still water contact right after application; can be applied by spray to horizontal, vertical and overhead surfaces and on to complex structural configurations.

Application Data Summary

Like all high performance coatings, Nu-Klad 105 must be applied as recommended to obtain the maximum protection for which this coating is formulated.

Physical Data

Colour	black
Components	2
Mixing ratio (by weight) resin cure	
Curing mechanism	chemical reaction between components
Volume solids	100%
VOC* EC SED 19999/13/EC	6g/kg (6g/l)
Number of coats	1
Coverage per unit	15-40 m² depending on surface and application method.
Specific gravity	1.14 kg/l (mixed product)
Flash points	°C °F
(Closed Cup)	•
resin	64 147
cure	64 147
OE ^ l & aeAPØ	
OE ^¦&læ0ÆGÁÁ	25 75

*VOC figures are quoted according to both the EC directive 19999/13/EC which are theoretically calculated figures and the UK PG6/23(92) Appendix 3 which are practically determined figures.

Concrete

All concrete surfaces to be coated must be strong and sound; must contain no additive or hardeners, and should not be treated with sealers or conventional curing compounds containing waxes, silicones or silicates. New slabs(horizontal surfaces) to be cured with Nu-klad 105 should have a float finish or broom finish as described in American Concrete Institute, specification 301. Finishing shall be within aClass A tolerance. Or existing slabs with a troweled finish, see surface preparation. Foamed surfaces should be adequately vibrated to minimize air pockets and holes. Suitable form facing material should be used to produce a smooth form finish as described in American Concrete Institute, Specification 301. Do not use form release agents based on oils, which will deposit a residue on the concrete. When Nu-Klad 10 is used as a curing compound, the forms should be removed within three days.

Surface preparation water-cured concrete or existing surfaces

Must be cured a minimum of 14 days under favorable temperature and moisture conditions and have attained 80% of it's final strength. When cured, surface must be abrasive blasted. As an alternative . in case abrasive blasting is not possible acid etching might be used. It must be oted that acid etching is not advised in case the Nu-Klad 105 is used with a coating system intended for immersion purposes. A suitable finished, abrasive blasted surface must have a uniform surface texture exposing fine aggregate resembling coarse sandpaper. Concrete surfaces which have been cured with conventional curing compounds or are contaminated with form oils must be completely cleaned by abrasive blasting. Acid etching is not acceptable, as it will not normally remove these contaminants.

Concrete to be cured with Nu-Klad 105

New concrete which will be cured with Nu-Klad 105 does not require blasting or etching. It only necessary to remove fins and projections from formed concrete. Ensure that all surfaces are free from oil or other contaminants. Nu-Klad 105 should be applies as soon as possible after pouring or finishing of concrete as described under **Application as a curing compound**.

Mixing

Nu-Klad 105 is packaged in 5 kg units of the proper proportions of resin and hardener which must be mixed together before use. A power mixer is recommended, such as 1/4 inch jiffy Mud and Resin Mixer chucked into a 1/4 inch or 3/8 inch variable speed drill with an explosion proof motor. Mix only full units, one at a time. Thoroughly stir both components before combining. Empty the hardener into the resin component container and mix thoroughly until the hardener has been completely dispersed. Immediately after mixing, Nu-Klad 105 is ready for use. For brush, roller or squeegee application, do not add any type of thinner. For airless spray application, Nu-Klad 105 can be thinned using up to 25% of OF ^\8\ aeA\PØ. When using airless spray, it maybe desirable to mix two units to provide sufficient material tofill the pump. Do ot mix more material than can be used within the working time one hour at 23 °C/73 °F. Nu-Klad 105 cures by chemical reaction between components. Combining more than two mixed units at one time, reduces working time. Material which has begun to set must be discarded

Application Data

	Substrate	concrete
	Application method	bush, roller, spray or squeegee
	Potlife (at 20°C/68°F)	1 hour
Initial setting time (at 20°C/68°F) 17 hours		
	Induction time (at 20°C/68°F).	not applicable

Environmental Conditions

Optimum temperatures for handling and using Nu-Klad 105 are between 18 and 27°C (64 and 81°F). Store material within this range for 48 hours prior to use. Below $18^{\circ}\text{C}/64^{\circ}\text{F}$ the application becomes more difficult and the coverage is reduced.

Nu-Klad 105 can be applied to concrete surfaces as cool as 10°C/90°F; although curing is retarded, typical properties of the cured Nu-Klad 105 will not be affected. It can be applied to concrete surfaces as warm as 32°C/90°F, however on vertical surfaces it may have a tendency to run or sag.

Thinner	OĘ ^¦&[æaÁJPØ
Cleaner	OE[^\&[æeAFGÁ

Application

remove all loose material, then moistened with water. On slabs, puddle areas of water must not remain. On formed surfaces no running water may be evident. For brush application, use pure bristle or nylon bristle brush; for roller application, use a short-nap mohair roller with a non degradable core. Apply a thin coat to the surface and work it in vigorously. Cross brushing or cross rolling is recommended. For spray application, airless equipment is recommended such as Graco Bulldog Hydro-Spray or similar with a 0,43 mm (0.17 inch) fluid tip. Material may be thinned with up to 25% OF ^1&F agAPØ. Apply a thin coat to the surface in parallel passes. overlapping each pass 50 percent. On slabs (horizontals) any primer/sealer which had puddle in low areas (depressions in concrete pane) must be brushed out during application. On formed surfaces (verticals) and any primer/sealer which runs or sags must be brushed out during application. One 5 kg unit of Nu-Klad 105 primer/ sealer will cover approximately 15-40 m². of the concrete surface. The coverage will vary depending upon the density or porosity denser the surface, the greater the coverage; the more porous the surface the surface the lower the coverage. An even wet coat must be applied over the entire surface. After overnight curing, the coated surface may vary in appearance. Areas which appear to have no evidence of primer/sealer indicate a high porosity. In these areas a second application is recommended. Surfaces not properly primed or

Apply Nu-Klad 105 over a damp surface. Abrasive blasted concrete must be thoroughly cleaned to

Application as a curing compound

sealed may result in bubbling of surface.

When used as a curing compound, Nu-Klad 105 must be applied to slabs (horizontals) immediately after the final finishing operation or upon disappearance of the 'sheen' of surface moisture. On formed surfaces (verticals), apply immediately after form is removed. (Forms should be removed within three days after concrete is poured). If there is any drying or appreciable loss of moisture, spray the surface with water and allow to reach a uniform damp condition with no excess water on the surface.

Clean-un

Immediately after use, clean all application equipment with OF ^\8[æ\FG\end{align*} G\end{align*} dent on temperature and quantities mixed.

Shipping Data

Packaging resincure	0
Shipping weight	approx. 5.6 kg
Shelf life	1 year from shipment date when stored indoors in unopened, original containers at 5 to 40°C (41 to 104°F).

Caution

Nu-Klad 105 resin and cure are combustible and may cause skin or eye irritation. Keep away from heat and open flame. Keep container closed. Use with adequate ventilation. Avoid prolonged breathing of vapor. If used in confined areas, circulate adequate fresh air continuously during application. Avoid contact with skin or eyes. Do not intake internally. In case of contact, immediately flush skin with plenty of water; for eyes, flush with plenty of water for 15 minutes and get medical attention. For specific information on hazardous ingredients, required ventilation, possible consequences of contact, and safety measures see Safety Data Sheet.

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

PPG warrants its products to be free from defects in material and workmanship. PPG's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at PPG's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

PPG makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall PPG be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by PPG, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

PPG's liability on any claim of any kind, including claims based upon PPG's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall PPG be liable for consequential or incidental damages.

Due to PPG's policy of continuous product improvement, the information contained in this Product
Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product
Data/Application Instructions always refer to the PPG Protective & Marine Coatings website at www.ppgpmc.com

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.

PPG Coatings Europe BV

www.ppgpmc.com