



# Amertext 2270 Textured Finish Coarse Water borne (Exterior/Interior)

## Product Data/ Application Instructions

- **Durable & weather resistant**
- **Good adhesion properties**
- **Almost odourless**
- **Excellent colour retention**
- **Ease of application**
- **Can be used inside and outside**
- **Economical & inexpensive to apply**
- **Excellent washability & scrubability**
- **Water vapour permeable**

This durable and attractive finish is based on an acrylic resin. The material is hard wearing, washable and fully resistant to aggressive exterior environments in industrial, coastal and wet interior conditions subject to humidity and condensation. This product is filled with graded natural stone. It is developed to give various textured finishes. Excellent colour retention makes Amertext 2270 a self finishing system.

### Typical Uses

can be used on Plaster, cementitious substrates, masonry, primed wood or steel etc. Good for outside walls, boundary walls or for inside use such as ceilings or features. Can be used safely in close proximity to the sea or other damp environments.

### Application data summary

For complete information on procedures, equipment and safety precautions, see the application instruction as accompanying shipment. Like all paints and coatings Amertext 2270 Textured Finish Coarse must be applied as recommend to obtain the maximum performance.

### Physical Data

Solid Content ..... Appr.76% (by weight)  
(Varies slightly according to colour)

Finish ..... Texture Coarse

Colours ..... See Color Card

Spreading rate ..... 0.8 - 1.5 m<sup>2</sup> /Kg

• Depending on colour, application method, surface condition & required texture.

#### Drying time:

To Touch ..... 2 hours  
To re-coat ..... 24 hours

• Depending on thickness & ambient conditions.

Thinners ..... Sweet Water

Flash Point ..... Non Flammable

Application method ..... Roller or Spray

Packing size ..... 25 Kg

Shelf life ..... 12 months

Storage ..... Out of sun light

Storage Temp ..... 5°C upto 40°C

# Amertext 2270 Textured Finish Coarse

---

## Surface Preparation

### a. Concrete,Plaster etc :

Neutralize as required. Fill and smooth. Prime to suit interior or exterior surfaces. Clean off all contamination,de dust.

#### Recommended Primers :

- OA 3587 Latex Primer Sealer or
- OA 3566 Acrylic Primer Undercoat.

### b. Steel :

Prepare and Prime in accordance with primer data sheet. ie. OA 3957 Red Oxide.

## Application Equipment

Roller or Air mix spray ( Hopper or Pressure System).

Texture can be varied by depth and application technique.

## Application Data

Substrate ..... Plaster, cementitious substrates, masonry, Primed wood or steel.

Application methods ..... Trowel float or  
Stainless Steel knife

#### Drying time

To Touch ..... 2 hours

To re-coat..... 24 hours

- Depending on application depth and ambient conditions

NOTE: . Allow for application losses. ie. conditions, surface irregularity, surface porosity and application method. Consult your OAL representative for specific recommendations.

Thinners..... Sweet water

# Amertext 2270 Textured Finish Coarse

---

## Application Procedure

Amertext 2270 Textured Finish Coarse is a one component product and packaged in 25 kg.

1. Mix material thoroughly.
2. Ventilation with air is required during application and drying.
3. Dilution with sweet water to be limited to the need to achieve workability or texture adjustment.
4. Texture can be varied by depth and application technique
5. Clean all equipment after application with water.

## Safety Instructions

1. Ventilate work area.
2. Check to ensure that fire or explosion risks are eliminated.
3. Cover all cuts or wounds.
4. Avoid inhaling or ingesting product. (Use mask and goggles for all spray applications).
5. Cover skin as much as possible.
6. Wash hands regularly. Use suitable soft soap.
7. Protect eyes. If product gets into eyes wash out with water until clear. Seek medical assistance.
8. In the event of accidental ingestion seek immediate medical assistance.
9. Take extra care when using airless spray equipment to avoid accidental injury.

## Shipping Data

Packaging .....	in 25 Kgs.
Storage .....	out of sun light.
Storage temperature.....	5°C up to 40°C.
Shelf life.....	1 year from shipment date when stored indoors in unopened, original containers at 5 to 40°C.

# Amertext 2270 Textured Finish Coarse

---

## Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

## Warranty

OAL warrants its products to be free from defects in material and workmanship. OAL's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at OAL's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to OAL in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify OAL of such non-conformance as required herein shall bar Buyer from recovery under this

## warranty.

OAL makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall OAL be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by OAL, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

## Limitation of Liability

OAL's liability on any claim of any kind, including claims based upon OAL's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim. In no event shall OAL be liable for consequential or incidental damages.

Due to OAL's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the OAL Protective & Marine Coatings website at [www.oasisameronpaints.com](http://www.oasisameronpaints.com)

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

## Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.

## Oasis Ameron Company Ltd

Dammam 2nd Industrial City  
P.O.Box 4926 | Al Khobar 31952  
Saudi Arabia  
Tel: +966 3 812 1300 | Fax : +966 3 812 1128  
Email: [sales@oasisameronpaints.com](mailto:sales@oasisameronpaints.com)  
[www.oasisameronpaints.com](http://www.oasisameronpaints.com)