



NC 108 Topcoat

Product Data

Description

Oasis Ameron NC 108 topcoat is based on alkyd-nitrocellulose combination especially formulated for use on soft, hard wood, wood based materials and steel substrate. It has good flexibility and good water resistance.

Recommended uses

After suitable sealer this product can be applied on soft, hard wood, wood based materials and steel.

Clear topcoat is recommended where wooden grains and transparency is needed.

Principal Properties :

1. High quality finish
2. Weather resistant
3. Good gloss retention.
4. Good scratch/abrasion resistance.
5. Good flow and drying properties.
6. Simple application

Application methods : Brush, Roller, Spray

Thin only as required to gain required penetration or suitable spray pattern with NC Thinner upto 50% for use on porous substrates.

Surface Preparation:

Surface to be free of any contamination. Surface shall be sanded and de-dusted prior to application of NC 108 Topcoat.

Physical Data

Volume Solids..... 32% (ASTM D2697)*

FinishMatt, Semi-Gloss & Gloss

Color..... Clear & Solid Colors

Spreading rate.

@ 20 microns DFT 16 m² /Lt

Drying time:

To Touch..... 10 - 20 minutes

To overcoat 2 Hour (Minimum).

- Depending on ambient conditions & surface absorption.

Thinners & Cleaner NC Thinner

Flash Point 7°C

Application method Spray

Packing sizeUSG

Shelf life12 months

Storage.....Out of sunlight

Temperature 5°C upto 40°C

Note : Allow for application losses. ie. conditions, surface irregularity, surface porosity and application method.

- * Volume solids is measured in accordance with ASTM-D-2697. Slight variations may occur due to colour and testing variances.